

## Technical Data Sheet

33.06.153E – 06/06

### ® GENAKOR 022R

#### Hard rubber lining to protect steel components On-site rubber lining

##### Description

GENAKOR 022R is a graphite-filled hard rubber lining based on polyisoprene rubber IR that may also be applied on site and vulcanised using steam. Depending on the requirements, the thickness of the rubber sheet may range between 3 - 5 mm.

##### Typical uses

GENAKOR 022R is recommended as a protective lining for structural components made of steel that are subjected to chemical exposure.

Its primary spectrum of application includes the lining of flue gas scrubbers in garbage incineration plants, as well as storage tanks and reaction vessels that are operated at high temperature ranges.

##### Properties

GENAKOR 022R is characterised by its excellent chemical resistance to alkaline and acidic media, with the exception of oxidising media.

GENAKOR 022R cannot be spark tested.

##### Chemical resistance

Information on the chemical resistance properties will be furnished on request.

##### Substrate

The substrate is steel. Structural components made of steel must meet the requirements specified in DIN EN 14879-1.

##### Surface pre-treatment

The steel surface must be blasted metallurgically white. The preparation degree Sa 2 ½ as specified in DIN EN ISO 12944-4 and the roughness degree "Medium (G)" as specified in DIN EN ISO 8503-1 must be achieved; minimum roughness  $R_z = 50 \mu\text{m}$ . After blasting the steel surface must be primed.

Stainless steel must be abrasive blasted with non-ferritic abrasives. Grey cast iron must be tempered in the autoclave prior to blast cleaning, in order to expel any inclusions of moisture.

##### Application

The GENAKOR 022R rubber lining system is composed of the single-component Primer 1, the single-component Primer 2, the single-component Vulkodurit adhesive LS3A and the GENAKOR 022R rubber sheet.

Spread the Primer1 and Primer 2 on the substrate and then apply two coats of the Vulkodurit adhesive LS3A. The rubber sheets are coated with the Vulkodurit adhesive LS3A and bonded to the substrate in accordance with the specifications contained in DIN 28055-1. A durable and solid bonding will be achieved by firmly pressing down the rubber sheet and the subsequent vulcanisation process.

##### Consumption

Primer 1	approx. 0.15 kg/m <sup>2</sup>
Primer 2	approx. 0.20 kg/m <sup>2</sup>
Vulkodurit adhesive LS3A	approx.0.25 kg/m <sup>2</sup> per coat

##### Packing

The following standard quantities are available:

Primer 1	23 kg
Primer 2	25 kg
Vulkodurit adhesive LS3A	16, 170 kg

##### Storage

The products shall be stored in a cool and dry place. With a storage temperature of 23°C the minimum shelf life is as follows:

GENAKOR 022R sheet < 15 °C	1 month
Primer 1	12 months
Primer 2	6 months
Vulkodurit adhesive LS3A	6 months

Higher temperatures will shorten the shelf life of this products. The packaging drums are to be kept tightly shut and are to be resealed each time material has been removed. All liquid products must be stored frost-free.

**Safety**

Adequate ventilation shall be provided during the execution of all work. Ventilation is compulsory for all work carried out in pits and closed rooms. All vapours that are produced during processing must be continuously suctioned off at floor or bottom level.

Only such amount of material effectively required to continue work is to be stored at the working place. The instructions for the prevention of fire and explosion are to be observed if required.

Please note and ensure that even smallest quantities of the individual components and/or prepared mixtures are not allowed to reach the sewerage.

All regulations for the prevention of accidents stipulated by the employer's liability assurance association, the regulations for the prevention of accidents prescribed at the site of application and the TRGS 507 „Surface treatment in rooms and tanks“, as well as the safety precautions listed on the packing (label) required by the provisions of the Hazardous Materials Ordinance shall be adhered to. The operating instructions pursuant to § 14 GefStoffV as well as the EC safety data sheets are to be complied with.

Technical data	Test specification	Unit	Parameter
Density	DIN EN ISO 1183-1	g/cm <sup>3</sup>	1.40 ± 0.02
Hardness	DIN 53505	Shore D	78 ± 5
Tensile strength *)	DIN 53504	MPa	≥ 20
Elongation at tear *)	DIN 53504	%	> 2
Adhesive strength	DIN EN 24624	MPa	≥ 6
max. surface pressure		MPa	10
max. service temperature		°C	100

\*) : The values were determined at 4 mm thick rubber samples.

The technical data contained herein represents the current state of our product knowledge and is intended to furnish general information regarding our products and their application spectrum. In view of the diversity and multitude of application possibilities, this data should be regarded solely as general information, which does not guarantee any specific properties and/or suitability of these products for each concrete case of application. Consequently, when ordering a product, please contact us for detailed information relative to the properties required for a specific application. Our technical service will, upon request, furnish a profile of characteristics for the concrete application without delay.

**KCH GROUP GmbH**

P.O. Box 11 63, D-56425 Siershahn

Phone: +49 (0) 2623-600-0 / Fax: +49 (0) 2623-600-433 / eMail: info@kch-group.com

تلفن: ۰۴-۲۲۶۴۶۷۸۳ و ۰۱۰-۲۲۶۳۰۶۰۸

شرکت کسری نماینده رسمی KCH آلمان