

Technical Data Sheet

33.07.100E – 02/07

® KERABUTYL RB

Soft rubber lining to protect steel and components On-site rubber lining

Description

KERABUTYL RB is a vulcanized soft rubber lining based on butylrubber (IIR). The thickness of the rubber sheet may range between 3 and 5 mm depending on the requirement.

Typical uses

KERABUTYL RB is employed for the protection of steel and concrete components that are exposed to chemical attack. The primary fields of application encompass linings of absorbers, ducts and supply vessels in flue gas desulphurization plants as well as production and storage tanks in the chemical industry.

Properties

KERABUTYL RB stands out for its excellent chemical resistance for example to acids, alkaline and saline solutions and offers a superior resistance to water vapour.

KERABUTYL RB also provides all the advantages of a vulcanized rubber sheet, particularly problem-free transportation and storage for 36 months as well as being fully capable of withstanding stress immediately after application without the necessity of costly vulcanization procedures.

Chemical resistance

Information on the chemical resistance properties will be furnished on request.

Substrate

Steel and concrete components may serve as substrate.

The steel structures and concrete components to be rubber lined shall comply with the requirements of DIN EN 14879-1.

Surface pretreatment

Steel: The steel surface must be blasted to a metallic white finish. A preparation degree of Sa 2 1/2 as specified in DIN EN ISO 12944-4 and a roughness degree of "medium (G)" as specified in DIN EN ISO 8503-1 must be achieved; minimum roughness $R_z = 50 \mu\text{m}$ (Segment 2). After blasting, the steel surface must be primed.

Concrete: If required the concrete substrate must be treated by means of blasting in such a way that it is free from cement slurries, cement skin, loose and brittle particles, defects and separating substances. The residual moisture of the concrete surface shall be $< 4\%$.

Concrete substrates are provided with a conductive smoothing coat (thickness approx. 1 mm) of KERAPOX EP 221 to level unevenness and to serve as counter pole for electrical tightness testing.

Application

The KERABUTYL RB rubber lining is composed of the single-component Primer 1 (on steel) and/or the single-component Keratex primer (on concrete), the three-component adhesive BS and the KERABUTYL RB sheet.

Mixing ratios	Parts by weight (kg)	Parts by volume (l)
Adhesive BS		
Solution BS	100	2.00
Accelerator BS	9	0.12
Keratex hardener E	3.4	0.06

Apply the Primer 1 on the steel substrate or spread the Keratex primer on the concrete substrate (KERAPOX EP 221). Then two coats of adhesive BS are applied on both the primed substrate and the rubber sheet.

The rubber sheets are firmly bonded to the substrate by means of rolling as specified in DIN 28055-1.

Pot life

Temperature	Adhesive BS
15°C	approx. 160 min
20°C	approx. 120 min
30°C	approx. 55 min

Consumption

Primer 1: approx. 0.15 kg/m²
Keratex primer: approx. 0.15 kg/m²
Adhesive BS: approx. 0.2 kg/m² per application

Packing

The following standard quantities are available:

Primer 1	23 kg
Keratex primer	5, 16 kg
Solution BS	5, 15 kg
Accelerator BS	5, 25 kg
Keratex hardener E	0.75 kg
KCH cleaner 1	8.5 kg

Storage

The products shall be stored in a cool and dry place. With a storage temperature of 23°C the minimum shelf life is as follows:

KERABUTYL RB sheet < 35°C	36 months
Primer 1	12 months
Keratex primer	12 months
Solution BS	12 months
Accelerator BS	12 months
Keratex hardener E	12 months
KCH cleaner 1	24 months

Higher temperatures will shorten the shelf life of this products. The packaging drums are to be kept tightly shut and are to be resealed each time material has been removed. All liquid products must be stored frost-free.

Safety

Adequate ventilation shall be provided during the execution of all work. Ventilation is compulsory for all work carried out in pits and closed rooms. All vapours that are produced during processing must be continuously suctioned off at floor or bottom level.

Only such amount of material effectively required to continue work is to be stored at the working place. The instructions for the prevention of fire and explosion are to be observed if required.

Please note and ensure that even smallest quantities of the individual components and/or prepared mixtures are not allowed to reach the sewerage.

All regulations for the prevention of accidents stipulated by the employer's liability assurance association, the regulations for the prevention of accidents prescribed at the site of application and the TRGS 507 „Surface treatment in rooms and tanks“, as well as the safety precautions listed on the packing (label) required by the provisions of the Hazardous Materials Ordinance shall be adhered to. The operating instructions pursuant to § 14 GefStoffV as well as the EC safety data sheets are to be complied with.

Technical data	Test specification	Unit	Parameter
Density	DIN EN ISO 1183-1	g/cm ³	1.25 ± 0.02
Hardness	DIN 53505	Shore A	55 ± 5
Tensile strength *)	DIN 53504	MPa	≥ 6
Elongation at tear *)	DIN 53504	%	≥ 500
Peeling strength	DIN 28055-2	N/mm	≥ 3
Max. surface pressure		MPa	2
Max. operating temperature		°C	100

*) : The values were determined at 4 mm thick rubber samples.

The technical data contained herein represents the current state of our product knowledge and is intended to furnish general information regarding our products and their application spectrum. In view of the diversity and multitude of application possibilities, this data should be regarded solely as general information, which does not guarantee any specific properties and/or suitability of these products for each concrete case of application. Consequently, when ordering a product, please contact us for detailed information relative to the properties required for a specific application. Our technical service will, upon request, furnish a profile of characteristics for the concrete application without delay.

KCH GROUP GmbH

P.O. Box 11 63, D-56425 Siershahn

Phone: +49 (0) 2623-600-0 / Fax: +49 (0) 2623-600-433 / eMail: info@kch-group.com

تلفن: ۰۴-۲۲۶۴۶۷۸۳ و ۰۱۰-۲۲۶۳۰۶۰۸

شرکت کسری نماینده رسمی KCH آلمان